

SHADES

Technical details

Manufacturing method	Tufted
Pile type	Looppile
Special treatment Kleenaway	Yes
Dyeing method	Solution dyed
Pile content	100 % PA Solution dyed
Gauge	1/10
Backing	Bitumen with glasfiberscrim
Pile weight	ca 600 g/m ²
Pile height	ca 6,0 mm
Total thickness	ca. 7,5 mm
Total weight	ca 4400 g/m ²
Tuft density	ca. 184000 /m ²
Dimension	50 x 100 cm
Flammability classification	Bfl S1 according to EN13501-1
Electrostatic properties	Walking Test ≤ 2,0 KV Resistance ≤ 10 ⁹
Suitability	EN1307 - 32 - Commercial general
Sound absorption	20 dB ISO 140-8
Colour fastness:	
To light	> 7 according to ISO 105B02
To rubbing	> 4 according to ISO 105-X12

48251	48232	48262
48250	48233	48260
48242	48224	48276
48240	48220	48270
48284	48230	48280



Maintenance

The fibre blend used has exceptional resistance to soiling and facilitates the use of recognised cleaning solutions.

This carpet must be sold and installed in accordance with BS5325. Chair mats are recommended for use under castor chairs.

All specifications are subject to normal commercial tolerances and subject to change where they improve the product's performance.

Pile reversal / shading

Carpets may be subject to permanent pile reversal, also known as "shading" or "water-marking".

The pile in certain areas may become distorted, giving the appearance of areas of light and shade. No specific cause of this has been identified and it is no manufacturing fault.

We reserve the right to make technical alterations and improvements to this product. Colour variations from the original sample can occur.

Installation



straight



wall



shuffle vertical



quarter



fishy



16

EN 1307

Manufactured by: TAPIBEL nv.
Industrielaan 4 - B-3900 Overpelt
DOP 000482-003 - EN 14041

SHADES TILES

For use as floor covering in buildings (EN 14041) according to the manufacturer's specifications