MYRAGE

Technical details

| Manufacturing method | Tufted |
|-----------------------------|--------------------------------|
| Pile type | Looppile - structured |
| Dyeing method | Solution Dyed |
| Pile content | 100% Polyamide |
| Gauge | 1/10 |
| Backing | Bitumen with glasfiberscrim |
| Pile weight | ca. 680 gr/m ² |
| Pile height | ca. 5,0 mm |
| Total thickness | ca. 7,5 mm |
| Total weight | ca. 4450 gr/m ² |
| Tuft density | ca. 180 000/m² |
| Dimension | 50 x 50 cm |
| Flammability classification | Bfl S1 according to EN13501-1 |
| Electrostatic properties | Walking Test < 2,0 KV |
| | Resistance ≥ 10 ¹⁰ |
| Suitability | EN1307 - 33 - Heavy Commercial |
| Sound absorption | ΔLw - 28 dB ISO 140-8 |
| Colour fastness : To light | ≥ 7 according to ISO 105-B02 |
| To rubbing | ≥ 4 according to ISO 105-X12 |
| Bleach resistance | Yes |

Maintenance

The fibre blend used has exceptional resistance to soiling and facilitates the use of recognised cleaning solutions.

This carpet must be sold and installed in accordance with BS5325. Chair mats are recommended for use under castor chairs.


All specifications are subject to normal commercial tolerances and subject to change where they improve the product's performance.

Pile reversal / shading

Carpets may be subject to permanent pile reversal, also known as "shading" or "watermarking".

The pile in certain areas may become distorted, giving the appearance of areas of light and shade. No specific cause of this has been identified and it is no manufacturing fault.

We reserve the right to make technical alterations and improvements to this product. Colour variations from the original sample can occur.



MYRAGE TILES For use as floor covering in buildings (EN 14041) according to the manufacturer's specifications

www.incati.be - sales@incati.be Tel : +32 11 80 48 50 - Fax: +32 11 64 75 46 Industrielaan 4 - Nolimpark 1319 B-3900 Overpelt - Belgium

EED[®]

Report 441633-01

Requirements fulfilled



Î NA

EN 1307

НСНО РСР

∫° DL