ATLANTIC

Technical details

Manufacturing method	Tufted
Pile type	Looppile
Dyeing method	Solution Dyed
Pile content	100% Polyamide
Gauge	1/10
Backing	Bitumen with glasfiberscrim
Pile weight	ca. 1000 gr/m ²
Pile height	ca. 5,5 mm
Total Thickness	ca. 6,5 mm
Total weight :	ca. 4500 gr/m²
Tuft density	ca. 182 500/m²
Dimension	50 x 50 cm
Flammability classification	Bfl S1 according to EN13501-1
Electrostatic properties	Walking Test < 2,0 KV
	Resistance ≥ 10 ¹⁰
Suitability	EN1307 - 33 - Heavy Commercial
Sound absorption	30 dB ISO 140-8
Colour fastness : To light	≥ 7 according to ISO 105-B02
To rubbing	≥ 4 according to ISO 105-X12
Bleach resistance	Yes

Maintenance

The fibre blend used has exceptional resistance to soiling and facilitates the use of recognised cleaning solutions.

This carpet must be sold and installed in accordance with BS5325. Chair mats are recommended for use under castor chairs.

All specifications are subject to normal commercial tolerances and subject to change where they improve the product's perfor-

Pile reversal / shading

Carpets may be subject to permanent pile reversal, also known as "shading" or "watermarking".


The pile in certain areas may become distorted, giving the appearance of areas of light and shade. No specific cause of this has been identified and it is no manufacturing fault.

We reserve the right to make technical alterations and improvements to this product. Colour variations from the original sample can occur.





Installation



































EN 1307

Manufactured by: TAPIBEL nv. Industrielaan 4 - B-3900 Overpelt

DOP 000576T-001 - EN 14041

ATLANTIC TILES

For use as floor covering in buildings (EN 14041) according to the manufacturer's specifications



